

### TECHNICAL DATA SHEET

---

#### PRODUCT DESCRIPTION:

Permathane® SM2100 is a high performance reactive silyl-modified adhesive sealant. It is a one-component moisture-cure sealant that exhibits excellent bond strength after cure. It imparts integral flexibility, superior adhesion and resistance to ultraviolet and infrared radiation. Ease of application, minimum shrinkage, fast skin formation, and primerless adhesion to most building materials and substrates make this an excellent choice for an all purpose sealant.

#### ADVANTAGE:

- Permanently flexible
- Easy to gun – Easy to tool
- Cures to a tough, durable, elastic consistency with excellent cut and tear resistance
- Paintable and stainable
- Primerless adhesion to substrates including galvanized steel, aluminum, concrete, glass, Galvalume®, Galvalume-PLUS®, Acrylume®, Zinalume®, Kynar 500®, vinyl, fiberglass and ABS.

#### TYPICAL USES:

- Sealing joints around windows and doors
- Back bedding compound for windows and doors
- Bonding RV and transportation sidewalls, windows, compartments and roofing
- Sealing corner moldings, fabricated roof-lap seams, bumper assemblies and body-to-cab joints in mini-motor homes
- Sealing butt and lap joints

#### LIMITATIONS:

##### Not recommended for:

- a) Unprimed masonry joints that will be subjected to continuous water immersion.
- b) On special architectural finishes without pretesting adhesion.
- c) Dynamic expansion joints.

##### Should not be applied to:

- a) Frost bearing surface or when temperature is below 40°F (4.45°C).
- b) Highly plasticized gasket compounds without proper testing.

#### Weatherability:

SM2100 High Performance Reactive Adhesive Sealant exhibits excellent weatherability when exposed to ultraviolet radiation, rain, infrared radiation, atmospheric hydrocarbons and extremes in temperature (1,000 hours QUV).

#### INSTALLATION:

Manual or air operated caulking gun or industrial pump system can be used. Hoses from pump and/or header system, and all seals/packings, must be of Teflon or polypropylene. Apply to clean dry surfaces. Cleaning of metal, glass or plastic surfaces should be a solvent wipe procedure or by mechanical means. Detergent or soap and water cleaning treatments are not recommended. Protective films must be removed by a solvent recommended by the manufacturer of the film or by other means which leave no residue. In all cases where used, solvents shall be applied with one clean cloth or lintless paper towel, and the solvent wiped clean with a second cloth or towel. Cleaning solvents should not be allowed to air dry or evaporate without wiping.

**ARCHITECTURAL COATINGS, PAINTS AND PLASTICS SHOULD BE CLEANED WITH SOLVENT APPROVED BY THE MANUFACTURER OF THAT PRODUCT. READ ALL LABELLING BEFORE USE, AND FOLLOW THE SOLVENT MANUFACTURER'S RECOMMENDATIONS AND INSTRUCTIONS FOR SAFE HANDLING.**

#### PRETEST FOR ADHESION:

Pretest for adhesion is intended to eliminate potential field problems by testing SM2100 with samples of building materials on which it will be applied. This testing will aid in determining the proper surface preparation method and effective solvents for cleaning prior to application.

#### CLEAN-UP:

The best method for clean-up of uncured SM2100 is the use of a clean dry rag. Wipe off any excess sealant then allow the residual to cure. Any residual sealant will appear hazy. This haze can be cleaned off using IPA or other suitable solvent. Cured sealant will need to be mechanically removed.

### SPECIFICATION COMPLIANCE:

SM2100 High Performance Reactive Adhesive Sealant meets the test requirements of:

<ul style="list-style-type: none"><li>▪ TT-S-00230 C (Type II) Class A,</li><li>▪ Non-sag, One-Component</li><li>▪ ASTM C 920 Type S, Grade NS, Class 25, Use-NT, A, M, G and O</li><li>▪ AAMA 805.2 Group C,</li><li>▪ AAMA 803.3</li><li>▪ AAMA 808.3</li></ul>
---

### TYPICAL PROPERTIES:

Characteristic	Result	Test Method
Composition:	Reactive Polymer	
Density, lb/ gal	12.88 lb/ gal	
Flash point	115°F (68.33°C)	
VOC	39.5 g/L	EPA Method 24
Percent Solids:	97% minimum	By weight
Extrusion Rate:	5-20 seconds Readings are the range of time required to deliver 20 grams of materials through a 0.104" orifice with 40 psi air pressure @ 77 °F ASTM D 2452	
Slump:	0.1" Maximum	AAMA 800
Hardness (Shore A):	25 - 35	AAMA 800 ASTM C661
Paintability:	Compatible with most alkyds, enamels and lacquers	
Odor:	Mild before cure; none after cure.	
Vehicle Migration:	Pass	AAMA 800
Tensile Strength:	200 psi	ASTM D412
Peel Strength: (glass/aluminum)	20 p.i.w. Minimum	AAMA 800 ASTM C794
Skin Time:	30 Minutes	1/4" dia. Bead @ 77°F ± 5°F, 50% RH
Cure Time:	24 Hours	
Elongation:	300% Minimum	ASTM D 412
Total joint movement	50%	ATM C 719
Service Temperature Range:	-40°F to 200°F (-40°C to 93.3°C)	

### COVERAGE:

1/16" (1.58MM) Diam. Bead .....6260 Ft. Gal.
1/8" (3.17mm) Diam. Bead.....1565 Ft. Gal.
3/16" (4.76mm) Diam. Bead ..... 695 Ft. Gal.

### PACKAGING:

- 50 gal. (182.95 liter) drums

### FREIGHT CLASSIFICATION:

SM2100 High Performance Adhesive Sealant is a non-regulated solid compound.

### SHELF LIFE:

SM2100 has a shelf life of twelve (12) months from date of manufacture when stored below 80°F (26.67°C)

### PRECAUTIONS:

IF THIS PRODUCT IS USED IN DIRECT CONTACT WITH ANY OTHER SEALANT, ELASTOMER, THERMAL-BREAK COMPOUND OR ARCHITECTURAL PAINT, A COMPATIBILITY TEST MUST BE CONDUCTED, BY PURCHASER OR USER, PRIOR TO ACCEPTANCE. The suitability of this product, for each intended use, must be determined by the purchaser prior to acceptance

### FIRST AID:

#### KEEP OUT OF REACH OF CHILDREN.

Avoid skin and eye contact. Avoid breathing of direct concentrated vapors. Use with adequate ventilation. On contact, uncured sealant could cause irritation on the skin and eyes. In case of eye contact flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed do not induce vomiting, call a physician. This product is manufactured for professional and industrial use only.

Refer to the Safety Data Sheet (SDS) for further information. For medical emergency only call ChemTrec 1800-424-9300

Galvalume and Galvalume-Plus are registered trademarks of BIEC International.

ACRYLUME is a registered trademark of United States Steel Corporation. Kynar 500 is a registered trademark of Arkema, Inc.

ZINCALUME is a registered trademark of BlueScope Steel Limited.

### EXCLUSION OF WARRANTIES:

AS TO THE HEREIN DESCRIBED MATERIALS, ITW POLYMERS SEALANTS NORTH AMERICA, INC. MAKES NO WARRANTIES WHETHER EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SINCE THE USE OF THE HEREIN DESCRIBED MATERIALS INVOLVES MANY VARIABLES IN METHODS OF APPLICATION, HANDLING AND/OR USE, THE USER IN ACCEPTING AND USING THESE MATERIALS ASSUMES ALL RESPONSIBILITY FOR THE END RESULT. THE PURCHASE OF THIS ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT IS SUBJECT TO THE TERMS AND CONDITIONS OF AN "AS IS" SALE, AND IF THE PRODUCT IS PROVED TO BE DEFECTIVE, THE EXCLUSIVE REMEDY, AT ITW POLYMERS SEALANTS NORTH AMERICA, INC.'S OPTION, SHALL BE TO REPLACE THE DEFECTIVE ITW POLYMERS SEALANTS NORTH AMERICA, INC. PRODUCT. ITW POLYMERS SEALANTS NORTH AMERICA, INC. SHALL NOT OTHERWISE BE LIABLE FOR LOSS OF DAMAGES, WHETHER DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL, REGARDLESS OF THE LEGAL THEORY ASSERTED, INCLUDING NEGLIGENCE, WARRANTY OR STRICT LIABILITY.

Complete technical information is available from  
ITW Polymers Sealants North America, Inc.